

聚丙烯樹脂

RECYCLED POLYPROPYLENE RESINS



概述

聚丙烯再生樹脂
消費後再生材料比例 100%

Description

Post-Consumer Recycled Polypropylene Resins.
Material from Post-Consumer Recycled sources 100%

特性

良好的加工性能

Characteristics

Good processability

應用

1. 押出
2. 改性

Applications

1. Extrusion
2. Modified

物理性質 Physical Properties

項目 Properties	試驗方法 Test Method	數 值 Typical Value
熔融指數 Melt Index (g/10min) 2.16kg / 230°C	ASTM D1238	2-3
密度 Density (g/cm ³)	ASTM D792	0.93-0.94
斷裂點抗張強度 Tensile Strength (MPa)	ASTM D638	>20
斷裂點伸長率 Elongation at Break (%)	ASTM D638	>200
硬度 (蕭氏 D)Hardness (Shore D)	ASTM D2240	66D
耐衝擊 IZOD impact strength (kg-cm/cm)	ASTM D256	7-13

據本公司所知，上述資料應屬正確無誤，惟因使用時之情況非受本公司管制，所以本公司對上述所作之一切建議，恕不負保證之責，以上數據為平均值，謹提供作為參考。The information contained herein is, to our best knowledge, true and accurate. However, since conditions of use are beyond our control, all risks of such use are assumed by users. This data sheet provides average test values, which are only for referential use. NB: The break type is no break. The above data are only for reference. The parameter is just for referential purpose only. In actual processing, the parameter should be adjusted by construction of mold, shape and size of product, and so on.

DATE : 2023.06.30

TYC ENVIRONMENTAL TECHNOLOGY CO., LTD. 域誠環保科技股份有限公司

Tel: 886-2-28851353 Fax: 886-2-28851320 Web: www.tyc-tw.com E-mail: info@tyc-tw.com
Address: No. 200, Zhulu Rd., Zhutang Vil., Zhutang Township, Changhua County 525, Taiwan 地址: 彰化縣竹塘鄉竹塘村竹鹿路200號